

PRODUCT INFORMATION

Chemical Base	Epoxy	
Packaging	Part A	20 kg containers
	Part B	5 kg containers
	Part A+B	25 kg ready to mix units
Appearance / Colour	Resin - part A	coloured, liquid
	Hardener - part B	transparent, liquid
Almost unlimited choice of colour shades.		
Shelf Life	24 months from date of production.	
Storage Conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.	
Density	Part A	~ 1.6 kg/l (DIN EN ISO 2811-1)
	Part B	~ 1.02 kg/l
	Mixed resin	~ 1.45 kg/l
	Filled resin 1 : 0,4	~ 1.66 kg/l
All Density values at +23 °C		
Solid content by weight	~100 %	
Solid content by volume	~100 %	

TECHNICAL INFORMATION

Shore D Hardness	~84 (14 days / +23°C)	(DIN 53 505)
Abrasion Resistance	45 mg (CS 10/1000/1000) (14 days / +23 °C)	(EN ISO 5470-1 Taber Abraser Test)
	Values have been determined using quartz sand F 34 (0.1-0.3 mm) from Quarzwerke GmbH Frechen sand.	
Compressive Strength	~77 N/mm ² (Resin filled 1:0.3 with F34*, 28 days / +23 °C)	(EN 13892-2)
Tensile Strength in Flexure	~41 N/mm ² (Resin filled 1:0.3 with F34*, 28 days / +23°C)	(EN 13892-2)
Tensile Adhesion Strength	> 1.5 N/mm ² (failure in concrete)	(ISO 4624)
Chemical Resistance	Resistant to many chemicals. Contact Sika technical service for specific information.	
Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 16 h	+100 °C
Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.)		
*No simultaneous chemical and mechanical exposure.		

SYSTEM INFORMATION

Systems	Please refer to the system data sheet of : Sikafloor® MultiDur ES-24 EQ Unicolour epoxy roller coat
----------------	---

APPLICATION INFORMATION

Mixing Ratio	Part A : part B = 80 : 20 (by weight)	
Consumption	~0.4–0.6 kg/m ² applied as a roller coating ~1.8–2.0 kg/m ² applied as a self-smoothing wearing course These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc. For detailed information, please refer to the System data sheet Sikafloor® MultiDur ES-24 EQ.	
Ambient Air Temperature	+15 °C min. / +30 °C max.	
Relative Air Humidity	80 % r.h. max.	
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.	
Substrate Temperature	+15 °C min. / +30 °C max.	
Substrate Moisture Content	<4 % pbw moisture content. Test method: Sika®-Tramex meter, CM-measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).	
Pot Life	Temperature	Time
	+15 °C	~ 45 minutes
	+20 °C	~ 30 minutes
	+30 °C	~ 15 minutes
Curing Time	Before overcoating Sikafloor®-266 CR allow:	
	Substrate temperature	Minimum Maximum
	+15 °C	24 hours 4 days
	+20 °C	12 hours 2 days
	+30 °C	6 hours 1 day

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Substrate Quality & Preparation

Please refer to Sika Method Statement: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

Application Instructions

Please refer to Sika Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

LIMITATIONS

- Do not apply Sikafloor®-266 CR on substrates with rising moisture
- Do not blind the primer.
- Freshly applied Sikafloor®-266 CR must be protected from damp, condensation and water for at least 24 hours.
- Avoid puddles on the surface with the primer.
- For exact colour matching, ensure the Sikafloor®-266 CR in each area is applied from the same control batch numbers.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall

refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 500 g/l (Limits 2010) for the ready to use product. The maximum content of Sikafloor®-266 CR is < 500 g/l VOC for the ready to use product.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 2 minutes until a uniform mix has been achieved. When parts A and B have been mixed, add the quartz sand 0.1 - 0.3 mm and mix for a further 2 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

Mixing Tools

Sikafloor®-266 CR must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

APPLICATION

Prior to application, confirm substrate moisture content, relative air humidity and dew point. If > 4 % pbw moisture content, Sikafloor® EpoCem® may be applied as a Temporary moisture barrier (T.M.B.) system.

Levelling

Rough surfaces need to be levelled first. Therefore use Sikafloor®-144 / -156 / -161 levelling mortar (see product data sheet).

Roller coating

Sikafloor®-266 CR as coating can be applied by short-piled roller (crosswise).

Textured coating

Sikafloor®-266 CR is applied with a serrated trowel and then back-rolled (crosswise) with a textured roller.

Wearing course smooth

Sikafloor®-266 CR is poured, spread evenly by means of a serrated trowel.

After spreading the material evenly, turn the serrated trowel and smooth the surface in order to achieve an aesthetically higher grade of finish.

Roll immediately (within max. 10 minutes of application) in two directions with a spiked roller to ensure even thickness and to remove entrapped air. To obtain the highest level of aesthetic finish, spike roll in two directions at a 90 degree angle, passing only once in each direction.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

MAINTENANCE

To maintain the appearance of the floor after application, Sikafloor®-266 CR must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always

PRODUCT DATA SHEET

Sikafloor®-266 CR

May 2021, Version 02.01

020811020020000117

refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA
Lahore Punjab 54792
Pakistan
phone: +92 42 3569 4266 - 67
fax: +92 42 3569 4268
<http://pak.sika.com/>

PRODUCT DATA SHEET

Sikafloor®-266 CR
May 2021, Version 02.01
020811020020000117

Sikafloor-266CR-en-PK-(05-2021)-2-1.pdf

