

## PRODUCT DATA SHEET

# Sika® ViscoCrete®-3110

High range superplasticizer and self-compacting

Concrete (SCC) Admixture

### DESCRIPTION

Sika® ViscoCrete®-3110 is a third generation polycarboxylate based superplasticizer for concrete. It has been particularly developed for use in ready mixed concrete to give extended slump retention and high strength development of normal grade concrete mixes.

Sika® ViscoCrete®-3110 is suitable for use in concrete mixes containing microsilica and other pozzolanic materials such as GGBS and fly ash. Suitable for use in hot and tropical climatic conditions.

### USES

Sika® ViscoCrete®-3110 is mainly used for the following applications:

- Production of site mixed and ready-mix concrete
- During hot weather the production of concrete with extended transportation or placing times
- Concrete requiring retained workability for extended periods
- Concrete with low water : cement ratio
- Concrete placing in congested steel reinforcement
- Self-compacting concrete
- Slim elements requiring a high standard of surface finish
- High performance / high strength concrete

### PRODUCT INFORMATION

<b>Chemical Base</b>	Aqueous solution of modified polycarboxylates, co-polymers
<b>Packaging</b>	200 L drums and 1000 L flow bins Bulk supply in tanker trucks is possible on request
<b>Appearance / Colour</b>	Brown liquid
<b>Shelf Life</b>	12 months from date of production if stored properly
<b>Storage Conditions</b>	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +45°C. Protect from direct sunlight and frost.

### CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-3110 acts by surface absorption on the cement particles producing steric hindrance as well as electrostatic repulsion between cement particles which results in higher dispersion, flow and retention.

Sika® ViscoCrete®-3110 provides the following beneficial properties:

- Self-compacting concrete (S.C.C.)
- High impermeability and strength due to extremely high water reduction
- Improved shrinkage and creep characteristics
- Excellent flowability resulting in minimal placing and compacting efforts
- Slower rate of carbonation and chloride ingress specially when silicafume or pozzolanic products are used
- Very good cost / performance ratio
- Does not contain chlorides or other steel corrosion promoting ingredients therefore may be used for reinforced and pre-stressed concrete construction

### APPROVALS / STANDARDS

Sika® ViscoCrete®-3110 follows the requirements of ASTM C494; Type G and EN 934-2

#### PRODUCT DATA SHEET

Sika® ViscoCrete®-3110  
May 2021, Version 01.01  
021301011000000198

## TECHNICAL INFORMATION

### Concreting Guidance

The standard rules of good concreting practice for production and placing must be observed when using Sika® ViscoCrete®-3110 in concrete. Refer to relevant standards.

Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

## APPLICATION INFORMATION

### Recommended Dosage

0.4 - 2.0 % by weight of binder  
Higher dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.

### Compatibility

Sika® ViscoCrete®-3110 may be combined with all types of Portland cement and the following Sika products:

SikaPump®

Sika® FerroGard®-901

SikaFume®

SikaFiber®

Sika Aer®

Sika® Stabilizer

Sika®-1 WT

We recommend to perform trial mixes to establish the required performance when combined with the above products. Please consult our Sika Technical Department.

### Dispensing

Sika® ViscoCrete®-3110 is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant. Do not add Sika® ViscoCrete®-3110 directly to the dry mix. For optimum utilization of its high water reduction property we recommend thorough mixing at a minimal wet mixing time of 60 seconds. The addition of the remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ure and intensive mixing.

Sika® ViscoCrete®-3110 should not be added to dry cement.

## LIMITATIONS

When using Sika® ViscoCrete®-3110 a mix design must be selected for the local material sources used and trial mixes performed to verify suitability.

If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperat-

Before pouring, suitability tests on the fresh concrete must be carried out. Due to the extended workability take special care that formwork is properly installed and secured. In case the setting time of concrete is extended, if cured properly, other properties may not be affected and higher ultimate strength is visualized. Sika® ViscoCrete® products are not compatible with admixtures based on sulfonated naphthalene or melamine.

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### **Sika Pakistan (Pvt.) Limited**

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

### **PRODUCT DATA SHEET**

Sika® ViscoCrete®-3110

May 2021, Version 01.01

021301011000000198

SikaViscoCrete-3110-en-PK-(05-2021)-1-1.pdf

