

# PRODUCT DATA SHEET

## Sarnavap<sup>®</sup>-2000 E

PE Vapour control layer

### DESCRIPTION

Sarnavap<sup>®</sup>-2000 E is an unsupported vapour control layer based on Polyethylene (PE).

### USES

- Vapour control layer for flat roofs

### CHARACTERISTICS / ADVANTAGES

- Ease and speed of installation
- Stays flexible at low temperatures
- Constant vapour diffusion resistance
- Recyclable (Delete if recycling facilities or recycling offerings are not available in local country)

### PRODUCT INFORMATION

<b>Chemical Base</b>	Low Density Polyethylene (PE-LD) foil / High Density Polyethylene (PE-HD) foil.	
<b>Packaging</b>	Packing unit	Refer to price list
	Roll length	25,00 m
	Roll width	4,00 m
	Roll weight	23,00 kg
<b>Appearance / Colour</b>	Surface	Smooth, PE-LD/HD foil
	Colour	Green
<b>Shelf Life</b>	5 years from date of production	
<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
<b>Product Declaration</b>	EN 13984	
<b>Visible Defects</b>	Pass	(EN 1850-2)
<b>Length</b>	25,00 m (± 2 %)	(EN 1848-2)
<b>Width</b>	4,00 m (± 1 %)	(EN 1848-2)
<b>Effective Thickness</b>	0,23 mm (± 10 %)	(EN 1849-2)

<b>Straightness</b>	Pass	(EN 1848-2)
<b>Mass per Unit Area</b>	230 g/m <sup>2</sup> (± 10 %)	(EN 1849-2)

## TECHNICAL INFORMATION

<b>Resistance to Impact</b>	≤ 100 mm	(EN 12691)
<b>Tensile Strength</b>	longitudinal ≥ 260 N/50 mm transversal ≥ 260 N/50 mm	(EN 12311-2)
<b>Elongation</b>	longitudinal ≥ 600 % transversal ≥ 600 %	(EN 12311-2)
<b>Tear Strength</b>	longitudinal ≥ 180 N transversal ≥ 180 N	(EN 12310-1)
<b>Reaction to Fire</b>	Class E	(EN ISO 11925-2:2002) (classification to EN 13501-1)
<b>Resistance to UV Exposure</b>	Not applicable for permanent exposure to UV irradiation.	
<b>Artificial Ageing</b>	Pass	(EN 1296 / EN 1931)
<b>Water Vapour Transimission</b>	≥ 300 m	(EN 1931)
<b>Water Tightness</b>	Pass	(EN 1928)

## SYSTEM INFORMATION

<b>System Structure</b>	The following products must be considered for use depending on roof design: <ul style="list-style-type: none"> <li>▪ Sarnavap® Tape F (for airtight sealing of overlaps)</li> <li>▪ Sarnatape® 20 (for airtight sealing of parapets, upstands, perimeters, penetrations, flashings)</li> <li>▪ Primer 130</li> </ul>
-------------------------	--

## APPLICATION INFORMATION

<b>Ambient Air Temperature</b>	-20 °C min. / +60 °C max.
<b>Substrate Temperature</b>	-30 °C min. / +60 °C max.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Sarnavap®-2000 E is not suitable as permanent waterproofing. It is not designed as a roofing membrane and therefore cannot replace the waterproofing membrane.
- The use of Sarnavap®-2000 E membrane is limited to geographical locations with average monthly minimum temperatures of -50 °C. Permanent ambient temperature during use is limited to +50 °C.
- The use of some ancillary products such as contact tapes and primer is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

# ECOLOGY HEALTH AND SAFETY

## REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Substrates shall be smooth, dry and strong enough to support foot traffic.

### SUBSTRATE PREPARATION

If substrate surfaces are rough (e.g. concrete or screed topping), install a levelling layer on top of substrate and underneath Sarnavap®-2000 E.

### APPLICATION METHOD / TOOLS

#### Installation procedure

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

#### Fixing method - General

Sarnavap®-2000 E is loose laid. It is light, so it must be covered immediately with the next layer of the roof build-up to avoid being removed by wind forces. If the vapour control layer is installed on a vertical surface the upper edge must be mechanically fixed (except at common base flashing height).

Sarnavap®-2000 E must be bonded airtight with Sarnatape® 20 to the warm side of the vertical construction.

#### Installation - General

1. Unroll the Sarnavap®-2000 E over the structural deck and temporarily weight in position.
2. Unroll the next roll of Sarnavap®-2000 E positioning to ensure a minimum 80 mm overlap with previous roll.
3. Fold back the top sheet of Sarnavap®-2000 E and apply Sarnavap® Tape F (jointing tape) to the bottom sheet.
4. Peel off release tape and carefully fold back the top sheet of Sarnavap®-2000 E ensuring no wrinkles or creases are formed.
5. Apply pressure to the top sheet of Sarnavap®-2000 E with a welding roller ensuring good adhesion to the Sarnavap® Tape F. On metal decks the lap should be fully supported in order to apply the correct bonding pressure.

### Overlaps

Contact surfaces of seams must be clean and dry for bonding. Adjoining sheets must overlap 80 mm. Seams are to be sealed tightly with Sarnavap® Tape F.

### Priming

When using Sarnatape® 20 jointing tape to form an airtight seal. Treat porous substrates with Primer 130 along tape bonding line.

### Transverse joints

An airtight bond is achieved by trimming the edge of the upper sheet at 45°.

### Parapets and upstands

Sarnavap®-2000 E must be carried up to the upper edge of the thermal insulation and sealed to the parapet / upstand / with Sarnatape® 20 jointing tape to form an airtight seal. If surface is rough, a layer of Sarnafil® Type T Felt must be used as a cushion layer.

### Perimeters and penetrations

Seal Sarnavap®-2000 E by turning up and sealing to a suitable smooth surfaced abutment with Sarnatape® 20.

### Flashings

Seal with Sarnatape® 20.

### Roof insulation

Standard construction practice requires that the vapour control layer at base flashing to extend to the top of the roof insulation and attached to the vertical construction.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal

#### PRODUCT DATA SHEET

Sarnavap®-2000 E

May 2021, Version 02.01

02094505100000010

in Baar.

**Sika Pakistan (Pvt.) Limited**  
141-CCA Phase IV, DHA  
Lahore Punjab 54792  
Pakistan  
phone: +92 42 3569 4266 - 67  
fax: +92 42 3569 4268  
<http://pak.sika.com/>

**PRODUCT DATA SHEET**  
**Sarnavap®-2000 E**  
May 2021, Version 02.01  
020945051000000010

Sarnavap-2000E-en-PK-(05-2021)-2-1.pdf

