

## PRODUCT DATA SHEET

## SikaEmaco® S 496

(formerly MEmaco S 496)

Ultra-high Strength, Non-shrink, Free Flowing Micro-Concrete for Structural Concrete Repairs

## DESCRIPTION

SikaEmaco® S 496 is a cementitious, pre-bagged, free flowing, one component, non-shrink precision micro-concrete with high early and ultimate strength. Suitable for use in hot and tropical climatic conditions.

## USES

SikaEmaco® S 496 precision micro-concrete is used for repair and grouting in various applications such as:

- Structural repair of deteriorated concrete
- Columns in precast construction Casting sections or members where the volumes required are too large for conventional grouts, and too small and inaccessible for normal concreting applications.
- Cavities, gaps and recesses
- Re-profiling of damaged concrete members and re-profiling of pile tops using formwork for both pouring and pumping techniques.

## CHARACTERISTICS / ADVANTAGES

SikaEmaco® S 496 is an easy to use precision micro-concrete requiring only the addition of water. It offers the following beneficial properties:

- Easy to mix
- Very good flow characteristics
- Adjustable consistency
- Reduced heat of hydration
- Shrinkage compensated
- Very High final strength
- Non-flammable
- Vapour permeable
- Excellent resistance to chloride ion ingress
- Compatible with the properties of typical concrete

## PRODUCT INFORMATION

Chemical Base	Portland cement, selected fillers and aggregates, special additives
Packaging	25 kg bag
Appearance / Colour	Grey powder
Shelf Life	12 months from date of production
Storage Conditions	Store in original unopened packaging in a cool and dry condition between +5°C and +35°C. Protect from direct sunlight, heat and moisture.
Maximum Grain Size	≤ 5 mm

## TECHNICAL INFORMATION

Compressive Strength	<b>+25°C</b>	<b>1 Day</b>	<b>7 Days</b>	<b>28 Days</b>	(EN 12390 Part 3)
	w/p = 0.15	≥ 25 N/mm <sup>2</sup>	≥ 65 N/mm <sup>2</sup>	≥ 90 N/mm <sup>2</sup>	
Chloride Ion Diffusion Resistance	≤ 500 Coulombs (cured 28 days)				(ASTM C1202)

## APPLICATION INFORMATION

Mixing Ratio	<b>Consistency</b>	<b>L water per 25 kg bag</b>	<b>Water / Powder Ratio</b>
	Flowable	3.25 - 3.75	0.13 - 0.15
Yield	~12.8 L / 25 kg bag		
Layer Thickness	Min. 50 mm per pour Max. 300 mm per pour Note: For repair areas greater than 300 mm thickness, aggregate "bulking" is required.		
Substrate Temperature	+10°C min. / +35°C max.		
Fresh mortar density	~2.2 kg/l (+25 °C)		

## BASIS OF PRODUCT DATA

- All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal reference - Version: MBS\_CC-UAE/Em\_S496\_01\_19

## LIMITATIONS

- Ensure formwork is secure and watertight to prevent movement and leaking during placing and curing.
- At high temperatures, use chilled water for mixing to keep the grout temperature below +32°C.
- In hot weather, base plates and foundations must be shaded from direct sunlight.
- Condition bags below 30°C prior to use.
- When maximum thickness exceeds 300 mm, the addition of dry, clean coarse aggregates is required (Sikadur®-510 AE or SikaEmaco® FL 100) the addition rate should be between 10 to 15 kg per each 25 kg of the dry micro-concrete powder. Trials are recommended to confirm suitability of aggregates to be employed.
- For additional information on SikaEmaco® S 496 or other grouting materials contact Sika Technical Department.

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

#### Concrete:

The repair area should be regular in shape with no sharp returns or internal corners and should be delineated with a 20 mm deep saw cut. The concrete shall be thoroughly clean, rough, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. De-laminated, weak, damaged and deteriorated concrete and, where necessary, sound concrete shall be removed by suitable means. Absorbent surfaces should be saturated thoroughly with clean water for minimum 24 hours.

The application of a suitable bonding agent, such as Sikadur®-32 LP, Sikadur® ADH 1414 or SikaTop® Armathec®-110 EpoCem®, will improve adhesion on large areas or where particularly dense concrete substrates are involved.

#### Steel Reinforcement:

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed. Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to SA 2.5 (ISO 8501-1) Embedded steel reinforcing should be treated with a suitable anticorrosion coating such as SikaTop® Armathec®-110 EpoCem® or SikaEmaco®-8100 AP. Reference shall be made to EN 1504-10 for specific requirements.

## MIXING

Add water according to the desired consistency into a clean mixing vessel before slowly adding the SikaEmaco® S 496 powder. SikaEmaco® S 496 is best mixed in a forced action mixer, for 2 to 3 minutes or until the mix is free of lumps, not longer than 5 minutes. Slow speed drill (maximum 500 rpm) can be also used for mixing. Normal tumble type concrete mixers are not suitable. Do not mix more grout than can be placed within 15 to 20 minutes. Do not add extra water or other ingredients. Mix only full bags for the best result.

**Note: Always start with minimum recommended quantity of water (water/powder ratio), only if required, gradually add water to desired consistency. Do not exceed maximum allowed limit of water per bag weight.**

## APPLICATION

Before pouring let the mixed grout stand for approximately 5 minutes after mixing to allow entrapped air to escape. Pour into the prepared area such that the grout has the shortest distance to travel. Ensure that air displaced by the grout is allowed to escape. When carrying out the base plate grouting, ensure a sufficient head of pressure to keep the mortar flowing. All exposed areas of the mortar surface should be kept as small as possible.

## CURING TREATMENT

Treatment of exposed surfaces with Sika® Antisol® range curing compound, is highly recommended for large areas of application. Use other approved curing methods such as polyethylene sheeting or wet hessian only for small exposed areas. Do not commence fogging until final set has been reached.

## CLEANING OF TOOLS

Clean equipment and mixer immediately after application with water. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

### Product Data Sheet

SikaEmaco® S 496

September 2025, Version 02.01

02030200000002113

SikaEmacoS496-en-PK-(09-2025)-2-1.pdf