

PRODUCT DATA SHEET

Sika® Antisol®-90

Concrete curing compound

DESCRIPTION

Sika® Antisol®-90 is a liquid curing compound for the prevention of premature water loss in concrete. Sika® Antisol®-90 has an efficiency index of 90 % when tested in accordance with the DoE Specification for Road and Bridge Works, clause 2709/1032.

USES

Sika® Antisol®-90 is applied to fresh concrete surfaces to form a fast drying, thin, flexible and tough impervious membrane which protects the concrete from rapid water evaporation during initial curing stages, thereby assisting towards obtaining maximum strength, durability and helping towards the elimination of shrinkage cracks and surface dusting.

Sika® Antisol®-90 is particularly useful in large areas of exposed concrete such as:

- Highways, runways and taxiways
- Aprons and hardstandings
- Roof decks
- Retaining walls
- Pre-stressed beams and piers
- Bridge decks, etc

CHARACTERISTICS / ADVANTAGES

- Application by hand or power-driven equipment - saves time, labour and money
 - Effective in all conditions of humidity and temperature
 - Single application, no further attention is required
 - The finish and colour of concrete are not affected once the compound has disintegrated under the influence of ultra violet light or abrasion
- Sika® Antisol®-90 provides the following beneficial properties to concrete surfaces:
- Reduces incidence of plastic cracking
 - Ensures achievement of desired strengths
 - Alleviates other costly methods such as hessian-watering, etc.
 - Reduces dusting
 - Minimises shrinkage

PRODUCT INFORMATION

Packaging	<ul style="list-style-type: none"> ▪ 20 L pail ▪ 200 L drum
Shelf Life	12 months from the date of production
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight.

APPLICATION INFORMATION

Yield	Sika® Antisol®-90 is applied at a rate of between 5.0–5.5 m ² per litre, depending on wind, humidity and temperature.
--------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Regular cleaning of spray equipment, especially the nozzle is recommended
- Sika® Antisol®-90 should only be used on surfaces exposed to normal weathering which will cause the eventual disintegration of the membrane
- Disintegration of the membrane will depend on many factors such as consumption rate, UV exposure, surface absorption, etc. As a guide, this process will take approximately 5 weeks
- Where subsequent surface treatment is to be undertaken before total disintegration of the membrane, the Antisol film must be removed

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

Sika® Antisol®-90 is supplied ready to use and should not be diluted with any forms of solvent. Stir well before use. Sika® Antisol®-90 is applied in a thin even coat, using spray equipment, onto the fresh concrete immediately after the free surface water has evaporated. After application of Antisol®-90, the area must be protected from rain for at least 3 hours. Drying time is ~30 minutes (at +30 °C to +35 °C)

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

PRODUCT DATA SHEET

Sika® Antisol®-90

July 2021, Version 01.01

021405031000000040