

# PRODUCT DATA SHEET

# Sikament® HRM Star PK

High Range Water Reducing, Retarding And Slump Retaining Concrete Admixture

#### **DESCRIPTION**

Sikament® HRM Star PK is used as a highly effective waterreducing agent and superplasticizer for the production of high quality, free flowing concrete in hot climates. The dual action of Sikament® HRM Star PK imparts excellent slump retention for prolonged periods, with high early and ultimate strengths. Suitable for use in tropical and hot climatic conditions.

#### **USES**

Sikament® HRM Star PK is used wherever high-quality concrete is demanded under difficult placing and climatic conditions.

## **CHARACTERISTICS / ADVANTAGES**

Sikament® HRM Star PK provides the following properties:

#### As a Superplastiziser

- Substantial improvement in workability without increased water or the risk of segregation.
- Long-lasting control of slump loss.
- No adverse effect on ultimate strengths.

#### As a Water Reducer

- Early strengths significantly increased.
- High ultimate strengths.
- ≥ 15% water reduction.
- Especially suitable for hot climates.
- No excessive air-entrainment.
- No adverse shrinkage effects.
- Improved surface finish.
- Increased water tightness.

# **APPROVALS / STANDARDS**

Sikament® HRM Star PK follows the requirments of ASTM C494; Type G.

#### PRODUCT INFORMATION

Chemical Base	Organic polymer blend
Packaging	05 ltr jerry can
	20 ltr plastic can
	200 ltr drum
	1000 ltr IBC
	Bulk supply in tanker is possible on demand
Shelf Life	12 months minimum from production date if stored properly in original unopened packaging
Storage Conditions	Store in a dry area between 5°C and 35°C. protect from direct sunlight.
Appearance / Colour	Brown Liquid
Specific gravity	~ 1.16 at 25°C

#### PRODUCT DATA SHEET

Sikament® HRM Star PK September 2023, Version 01.03 021302011000001256

Solid content by weight	~ 30 %	
pH-Value	~ 5-8 at 25°C	
Total Chloride Ion Content	Nil	

#### APPLICATION INFORMATION

Recommended Dosage	0.8-3% by weight of cement. It is advisable to carry out trial mixes to establish the exact dosage rate required.
Dispensing	Sikament® HRM Star PK can be added separately to the freshly mixed concrete or directly to the mixing water prior to its addition to the aggregates When added separately to the freshly mixed concrete, further mixing should take place for at least one minute per cubic meter.
Compatibility	Sikament® HRM Star PK may be combined with the following Sika products:  SikaPump Sika FerroGard-901 SikaFume It is also compatible with sulphate resistant cement. Pre-trials are recommended if combinations with the above products are being made. Please consult our Technical Services

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### **ECOLOGY HEALTH AND SAFETY**

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

#### **CLEANING OF TOOLS**

Clean all equipment and tools with water immediately after use.

#### **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA Lahore Punjab 54792 Pakistan phone: +92 42 3569 4266 - 67 fax: +92 42 3569 4268 http://pak.sika.com/

#### Sika Pakistan (Pvt.) Limited 141-CCA Phase IV. DHA

Lahore Punjab 54792 Pakistan phone: +92 42 3569 4266 - 67 fax: +92 42 3569 4268 http://pak.sika.com/

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SikamentHRMStarPK-en-PK-(09-2023)-1-3.pdf

