

PRODUCT DATA SHEET

Sikadur®-32 LP

Epoxy structural bonding agent for use at high temperatures

DESCRIPTION

Sikadur®-32 LP is a 2-part, epoxy based structural bonding agent for use at high temperatures. It is moisture tolerant and can bond wet or dry materials to damp or dry substrates.

USES

Sikadur®-32 LP may only be used by experienced professionals.

As a structural bonding agent and adhesive for:

- Concrete elements (including bonding fresh to hardened concrete)
- Hard natural stone
- Ceramics, fibre-cement
- Mortar, Bricks, Masonry, Render
- Steel, Iron, Aluminium
- Wood
- Polyester / fibreglass and epoxy resin materials
- Glass

CHARACTERISTICS / ADVANTAGES

- Application temperature range +20 °C to +40 °C
- Thickness up to 1 mm
- Easy to mix and apply
- Suitable for dry and damp concrete substrates
- Very good adhesion to many construction materials
- Hardens without shrinkage
- Different coloured parts (for mixing control)
- No primer needed
- High initial and ultimate mechanical strengths
- Impermeable to liquids and water vapour

ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 IEQc 4.1: Low-Emitting Materials - Adhesives and Sealants

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 1504-4 - Structural bonding

PRODUCT INFORMATION

Chemical Base	Epoxy resin and selected fillers	
Packaging	Parts A+B	5 kg ready to mix unit Pallets of 390 units (450 kg)
	Parts A+B	1,2 kg ready to mix unit Box of 6 units (7,2 kg)
	Refer to current price list for packaging variations	
Colour	Part A	white
	Part B	dark grey
	Parts A+B mixed	concrete grey
Shelf Life	24 months from date of production	

Storage Conditions

The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.

Density

Mixed resin ~1,4 ± 0,1 kg/l
Value at +23 °C.

Product Declaration

EN 1504-4: Structural bonding

TECHNICAL INFORMATION**Compressive Strength**

	Curing time	Curing temperature			(ASTM D 695-95)
		+23 °C	+30 °C	+40 °C	
1 day	–	~2 N/mm ²	~30 N/mm ²		
3 days	~14 N/mm ²	~24 N/mm ²	~41 N/mm ²		
7 days	~34 N/mm ²	~38 N/mm ²	~52 N/mm ²		
14 days	~39 N/mm ²	~43 N/mm ²	~56 N/mm ²		

Compressive strength at 4 % elongation

Modulus of Elasticity in Compression

~2100 N/mm² (14 days at +23 °C) (ASTM D 695-95)

Tensile Strength in Flexure

	Curing time	Curing temperature			(DIN EN ISO 178)
		+23 °C	+30 °C	+40 °C	
1 day	–	–	~18 N/mm ²		
3 days	~21 N/mm ²	~20 N/mm ²	~30 N/mm ²		
7 days	~24 N/mm ²	~28 N/mm ²	~36 N/mm ²		
14 days	~38 N/mm ²	~38 N/mm ²	~42 N/mm ²		

Modulus of Elasticity in Flexure

~2600 N/mm² (14 days at +23 °C) (DIN EN ISO 178)

Tensile Strength

	Curing time	Curing temperature			(ISO 527)
		+23 °C	+30 °C	+40 °C	
1 day	–	–	~11 N/mm ²		
3 days	~13 N/mm ²	~16 N/mm ²	~18 N/mm ²		
7 days	~20 N/mm ²	~18 N/mm ²	~22 N/mm ²		
14 days	~22 N/mm ²	~24 N/mm ²	~25 N/mm ²		

Modulus of Elasticity in Tension

~2750 N/mm² (14 days at +23 °C) (ISO 527)

Elongation at Break

1,0 ± 0,1 % (14 days at +23 °C) (ISO 527)

Shrinkage

Hardens without shrinkage.

Tensile Adhesion Strength

Curing time	Substrate	Curing temperature	Adhesion strength	(EN ISO 4624, EN 1542, EN 12188)
7 days	Concrete moist	+23 °C	> 3 N/mm ² *	
1 day	Steel	+23 °C	~8 N/mm ²	
3 days	Steel	+23 °C	~12 N/mm ²	
3 days	Steel	+30 °C	~13 N/mm ²	
3 days	Steel	+40 °C	~15 N/mm ²	

*100% concrete failure

Coefficient of Thermal Expansion

11,4 × 10⁻⁵ 1/K (EN 1770)
(linear expansion between +23 °C and +60 °C)

Heat Deflection Temperature

Curing time	Curing temperature	HDT	(ISO 75)
7 days	+23 °C	+49 °C	

(thickness 10 mm)

APPLICATION INFORMATION**PRODUCT DATA SHEET**

Sikadur®-32 LP

March 2025, Version 02.01

020204030010000120

BUILDING TRUST



Mixing Ratio	Part A : Part B = 2 : 1 by weight or volume		
Consumption	~1,3 kg/m ² per mm of thickness. This figure is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
Layer Thickness	~1 mm max.		
Sag Flow	Non-sag up to 1,0 mm thickness on vertical surfaces		(EN 1799)
Product Temperature	+20 °C min. / +40 °C max.		
Ambient Air Temperature	+20 °C min. / +40 °C max.		
Dew Point	Beware of condensation. Steel substrate temperature during application must be at least +3 °C above dew point.		
Substrate Temperature	+20 °C min. / +40 °C max.		
Substrate Moisture Content	Cementitious substrates must be dry or matt damp (no standing water). Brush the adhesive well into the substrate if matt damp.		
Pot Life	Temperature	Potlife*	Open time
	+20 °C	~145 minutes	~270 minutes
	+30 °C	~55 minutes	~240 minutes
	+40 °C	~35 minutes	~120 minutes
<small>*200 g The potlife begins when Parts A+B are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into smaller quantities. Another method is to chill Parts A+B before mixing (not below +5 °C).</small>			

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, when using adhesive for structural applications, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20–25 % of the failure load. A structural engineer must be consulted for design calculations for specific structural applications.
- When using multiple units during application, do not mix the following unit until the previous one has been used in order to avoid a reduction in workability and handling time.
- For heavy components positioned vertically or overhead, provide temporary support.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Concrete / masonry / mortar / stone

Concrete and mortar must be at least 3–6 weeks old. Substrate surfaces must be sound, clean, dry or matt damp. Free from standing water, ice, dirt, oil, grease, coatings, laitance, efflorescence, old surface treatments, all loose particles and any other surface contaminants that could affect adhesion of the bonding agent.

Steel

Surfaces must be clean, dry, free from oil, grease, coatings, rust, scale, all loose particles and any other surface contaminants that could affect adhesion of the bonding agent.

Wood

Substrate surfaces must be sound, clean, dry and free from dirt, oil, grease, coatings, all loose particles and any other surface contaminants that could affect adhesion of the bonding agent.

Polyester / epoxy / ceramics / glass

Surfaces must be clean, dry, free from oil, grease and any other surface contaminants that could affect adhesion of the bonding agent.

SUBSTRATE PREPARATION

Concrete / masonry / mortar / stone

Substrates must be prepared mechanically using suitable abrasive blast cleaning, needle gunning, light scabbling, bush hammering, grinding or other suitable equipment to achieve an open textured gripping surface profile.

PRODUCT DATA SHEET

Sikadur®-32 LP

March 2025, Version 02.01

020204030010000120

Steel

Surfaces must be prepared mechanically using suitable abrasive blast cleaning, grinding, rotating wire brush or other suitable equipment to achieve a bright metal finish with a surface profile to satisfy the necessary tensile adhesion strength requirement. Avoid dew point conditions before and during application.

Wood

Surfaces must be prepared by planing, sanding or other suitable equipment.

Polyester / epoxy

Surfaces must be prepared by abrading using suitable equipment.

Ceramics / glass

Surfaces must be prepared by abrading using suitable equipment. Do not apply to siliconised substrates.

All substrates

All dust and loose material must be completely removed from all substrate surfaces before application of the product by vacuum / dust removal equipment.

MIXING

Prior to mixing all parts, mix part A (resin) briefly using a mixing spindle attached to a slow speed electric mixer (max. 300 rpm). Add part B (hardener) to part A and mix parts A+B continuously for at least 3 minutes until a uniformly coloured smooth consistency mix has been achieved. To ensure thorough mixing pour materials into a clean container and mix again for approximately 1 minute. Over mixing must be avoided to minimise air entrainment. Mix full units only. Mixing time for A+B = 4,0 minutes. Mix only the quantity which can be used within its pot life.

APPLICATION METHOD / TOOLS

Apply the mixed Sikadur®-32 LP to the prepared substrate by brush, roller, spray or trowel ensuring uniform and complete coverage.

For optimum adhesion, it is recommended to apply adhesive to both substrates that require bonding.

On damp prepared concrete substrates, always apply by brush and work the product well into the substrate.

For bonding wet fresh concrete to hardened prepared concrete, place the concrete whilst the Sikadur®-32 LP layer is still 'tacky'. If the product becomes glossy and loses 'tackiness', apply another coat of Sikadur®-32 LP and proceed to place concrete.

CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened material can only be mechanically removed.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

PRODUCT DATA SHEET

Sikadur®-32 LP

March 2025, Version 02.01

020204030010000120

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sikadur-32LP-en-PK-(03-2025)-2-1.pdf