

PRODUCT DATA SHEET

Sikagard®-700 S PK

Siloxane based water repellent impregnation

DESCRIPTION

Sikagard®-700 S PK is a one part water repellent impregnation for absorbent cementitious substrates. It penetrates well into the open pores of the substrate, providing durable water repellency, while still allowing water vapour diffusion in both directions. Sikagard®-700 S PK complies with the requirements of EN 1504-2 for hydrophobic Impregnation (penetration depth class I)

USES

Sikagard®-700 S PK is used as water repellent and colourless protective surface treatment on absorbent exposed materials such as concrete, cementitious rendering, concrete tiles, fibre cement, brickwork (clay and lime sand, non-vitrified), natural stone.

Sikagard®-700 S PK can also be used as hydrophobic primer under solvent based or emulsion protective coating

Sikagard®-700 S PK is used as water-repellent impregnation (hydrophobic treatment) for absorbent substrates such as concrete in civil engineering or building concrete structures

- Suitable for protection against ingress (Principle 1, method 1.1 of EN 1504-9),
- Suitable for moisture control (Principle 2, method 2.1 of EN 1504-9)
- Suitable for increasing the resistivity (Principle 8, method 8.1 of EN 1504-9)

PRODUCT INFORMATION

Chemical Base	Silanes/Siloxanes blend in organic solvent.
Packaging	1000 ltr IBC 200 ltr drum 20 ltr plastic can 5 ltr jerry can
Appearance / Colour	Colourless liquid

CHARACTERISTICS / ADVANTAGES

- Reduction of capillary water absorption.
- Reduces efflorescence.
- Reduces dirt penetration into the pores.
- Improves thermal insulation.
- Can be overcoated with solvent based and dispersion coating.
- Higher durability and resistance than conventional silicone based treatments.
- Does usually not change the appearance of the substrate.
- Reduces chloride ion ingress and movement.
- Does not act as a vapour barrier.

APPROVALS / STANDARDS

- Tested by LPM -qualification test to SIA 162/5, Report A-13719-2 dated April 1993 – Water absorption, penetration depth, alkali resistance, water vapour diffusion.
- Conformity to the requirements of the EN 1504-2 class I – MPL, Sika Tüffenwies dated September 2008
- Hydrophobic impregnation according to EN 1504-2

Shelf Life	12 months from date of production if stored in unopened, undamaged and original sealed packaging.
Storage Conditions	Store in dry and cool conditions. Protect from moisture.
Flash Point	Closed cup: ~30°C (~86°F)
Specific gravity	~ 0.8 kg/l (25° C)

APPLICATION INFORMATION

Consumption	~ 0.300–0.500 kg/m ² (0.375–0.625 l/m ²) per coat for normally absorbent substrate. In order to ensure durability, a minimum of 2 coats must be applied.
Ambient Air Temperature	+5 °C min. / +30 °C max.
Substrate Temperature	+5 °C min. / +30 °C max.
Substrate Moisture Content	<5-6% when measured with Tramex method
Waiting Time / Overcoating	Can be overcoated with water/solvent based polymer paints - contact the paint manufacturer for details. When overcoating with Sikagard® or SikaColor® Emulsion or solvent based coating, wait at least 5 hours after the hydrophobic impregnation

SYSTEM INFORMATION

System Structure	1–2 x Sikagard®-700 S PK
-------------------------	--------------------------

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

USES

- Minimum age of concrete or mortar: at least 4 weeks.
- Cannot be overcoated with limewash or cement paint.
- If there are strict aesthetic requirements (often when used on natural stone), it is recommended to perform preliminary tests as on some stones a slight darkening of the surfaces may result.
- Sikagard®-700 S PK is not intended for waterproofing under hydrostatic pressure, in permanent contact with water, or for below grade waterproofing.
- Sikagard®-700 S PK is not intended to seal visible cracks from moisture ingress.
- Building components not to be coated (e.g. aluminium frames, windows etc.) need to be protected from contact with Sikagard®-700 S PK. In case of splashes, clean immediately using an additional solvent if necessary.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Free of dust, oil, efflorescence and existing paint coatings. Cracks in concrete of more than 200 µm must be repaired prior to application of the hydrophobic treatment.

Cleaning is best achieved by brushing with suitable detergents or by light blastcleaning or steam cleaning etc.

Best results are obtained on dry, very absorbent substrates. The substrate must look dry with no damp patches.

MIXING

Sikagard®-700 S PK is supplied ready for use and should not be thinned

APPLICATION

Sikagard®-700 S PK is applied using low pressure spray, brush or roller, working from bottom up taking care not to let the product run. Apply subsequent coats "wet on wet".

CLEANING OF TOOLS

Clean all tools and application equipment with whit spirit immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA
Lahore Punjab 54792
Pakistan
phone: +92 42 3569 4266 - 67
fax: +92 42 3569 4268
<http://pak.sika.com/>

Product Data Sheet

Sikagard®-700 S PK
August 2026, Version 01.01
020303210000000033

Sikagard-700SPK-en-PK-(08-2026)-1-1.pdf