

## PRODUCT DATA SHEET

# SikaWrap®-600 C

Stitched unidirectional carbon fibre fabric, designed for structural strengthening applications as part of the Sika® strengthening system

### DESCRIPTION

SikaWrap®-600 C is a unidirectional stitched, non-woven heavy carbon fibre fabric with mid-range strength, designed for installation using the wet application process.

### USES

SikaWrap®-600 C may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Replacing missing steel reinforcement
- Increasing the strength and ductility of columns
- Increasing the loading capacity of structural elements
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards

### PRODUCT INFORMATION

<b>Construction</b>	Fibre orientation	0° (unidirectional)
	Warp	Black carbon fibres 96 %
	Weft	E-Glass 2 %
	Stitch Yarn	Polyester stitch 1 %
	Binder	EP Powder 1 %
<b>Fibre Type</b>	Selected mid-range strength carbon fibres	

### CHARACTERISTICS / ADVANTAGES

- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating of different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Low density for minimal additional weight
- Extremely cost effective in comparison to traditional strengthening techniques

### APPROVALS / STANDARDS

- Avis Technique N° 3/16-875 (annule et remplace N° 3/10-669) Sika® CarboDur®, SikaWrap®
- CIT n°290 18/07/2017 (certificato di idoneità tecnica all'impiego) ; Sika® CarboDur®, SikaWrap®, Sikadur®

<b>Packaging</b>	<b>Fabric length per roll</b>	<b>Fabric width</b>
	2 rolls in a cardboard box ≥ 50 m	300 mm
<b>Shelf Life</b>	24 months from date of production	
<b>Storage Conditions</b>	Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight.	
<b>Dry Fibre Density</b>	1.81 g/cm <sup>3</sup>	
<b>Dry Fibre Thickness</b>	0.331 mm (based on fibre content)	
<b>Area Density</b>	600 g/m <sup>2</sup> ± 30 g/m <sup>2</sup> (carbon fibres only)	
<b>Dry Fibre Tensile Strength</b>	3 800 N/mm <sup>2</sup>	(ISO 10618)
<b>Dry Fibre Modulus of Elasticity in Tension</b>	242 000 N/mm <sup>2</sup>	(ISO 10618)
<b>Dry Fibre Elongation at Break</b>	1.43 %	(ISO 10618)

## TECHNICAL INFORMATION

<b>Laminate Nominal Thickness</b>	0.331 mm		
<b>Laminate Nominal Cross Section</b>	331 mm <sup>2</sup> per m width		
<b>Laminate Tensile Strength</b>	<b>Average</b>	<b>Characteristic</b>	(EN 2561*)
	3 000 N/mm <sup>2</sup>	2 400 N/mm <sup>2</sup>	(ASTM 3039*)
<b>Laminate Modulus of Elasticity in Tension</b>	<b>Average</b>	<b>Characteristic</b>	(EN 2561*)
	225 kN/mm <sup>2</sup>	200 kN/mm <sup>2</sup>	(ASTM 3039*)
* modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series			
<b>Laminate Elongation at Break in Tension</b>	1.33 %	(based on EN 2561)	(based on ASTM 3039)
<b>Tensile Resistance</b>	<b>Average</b>	<b>Characteristic</b>	(based on EN 2561)
	990 N/mm	792 N/mm	(based on ASTM 3039)
<b>Tensile Stiffness</b>	<b>Average</b>	<b>Characteristic</b>	(based on EN 2561)
	74.3 MN/m	66.0 MN/m	(based on ASTM 3039)
	74.3 kN/m per ‰ elongation	66.0 kN/m per ‰ elongation	

## SYSTEM INFORMATION

<b>System Structure</b>	The system build-up and configuration as described must be fully complied with and may not be changed.	
	Concrete substrate adhesive primer	Sikadur®-330 or Sikadur®-300
	Impregnating / laminating resin	Sikadur®-300
	Structural strengthening fabric	SikaWrap®-600 C

For detailed information on Sikadur®-330 or Sikadur®-300, together with the resin and fabric application details, please refer to the Sikadur®-330 or Sikadur®-300 Product Data Sheet and to the relevant Method Statement.

## APPLICATION INFORMATION

<b>Consumption</b>	<b>Wet application with Sikadur®-300</b>	
	First layer including primer	0.8–1.2 kg/m <sup>2</sup>
	Following layers	0.85–1.0 kg/m <sup>2</sup>
	<b>Application with Sikadur®-330 as primer and Sikadur®-300</b>	
Primer	0.4–0.6 kg/m <sup>2</sup>	
Fabric layers	0.85–1.0 kg/m <sup>2</sup>	

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

### Method Statements

Ref. 850 41 03: SikaWrap® manual wet application

Ref. 850 41 04: SikaWrap® machine wet application

## LIMITATIONS

- SikaWrap®-600 C shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-600 C fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-600 C can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional protection against UV light in exposed areas use Sikagard®-550 W Elastic, Sikagard® ElastoColor-675 W or Sikagard®-680 S.
- Please refer to the Method Statement of SikaWrap® manual wet application (Ref. 850 41 03) or SikaWrap® machine wet application (Ref. 850 41 04) for further information, guidelines and limitations.

## ECOLOGY HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Minimum substrate tensile strength: 1.0 N/mm<sup>2</sup> or as specified in the strengthening design.

Please also refer to the relevant Method Statement for further information.

### SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Please also refer to the relevant Method Statement for further information.

### APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-600 C is applied using the wet application process.

Please refer to the relevant Method Statement for details on the impregnating / laminating procedure.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must

### PRODUCT DATA SHEET

SikaWrap®-600 C

May 2021, Version 02.01

020206020010000045

be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

**Sika Pakistan (Pvt.) Limited**

141-CCA Phase IV, DHA  
Lahore Punjab 54792  
Pakistan  
phone: +92 42 3569 4266 - 67  
fax: +92 42 3569 4268  
<http://pak.sika.com/>

**PRODUCT DATA SHEET**

SikaWrap®-600 C  
May 2021, Version 02.01  
020206020010000045

