

PRODUCT DATA SHEET

SikaGrout[®]-114 PK

Cementitious, Shrinkage Compensated, General Purpose Grout

DESCRIPTION

SikaGrout[®]-114 PK is a cementitious, free flowing, economical, general purpose, non-shrink precision grout with high ultimate strength. Suitable for use in hot and tropical climatic conditions.

USES

SikaGrout[®]-114 PK is used for grouting in the following:

- Machine foundations
- Columns in pre-cast construction
- Concrete anchors, cavities, gaps, and recesses
- Base plates
- General concrete repairs
- Bridge bearing pads

PRODUCT INFORMATION

Chemical Base	Portland cement, selected fillers and aggregates, special additives
Packaging	25 kg bag
Shelf Life	6 months minimum from date of production
Storage Conditions	Store in original unopened packaging in cool and dry condition between 5°C and 35 °C. Protect from direct sunlight, heat and moisture.
Appearance / Colour	Grey Powder
Maximum Grain Size	Max 4 mm

TECHNICAL INFORMATION

Compressive Strength	ASTM C109		
	1 Day	3 Days	28 Days
	≥ 30 MPa	≥ 45 MPa	≥ 65 MPa
Modulus of Elasticity in Compression	35,000 N/mm ²		

CHARACTERISTICS / ADVANTAGES

SikaGrout[®]-114 PK is easy to use grout requiring only the addition of water. It offers the following beneficial properties:

- Easy to mix
- Good flow characteristics
- Adjustable consistency
- High final strengths
- Non-corrosive and iron-free

APPROVALS / STANDARDS

SikaGrout[®]-114 PK Follow the CRD-C621-83-10.2 and ASTM C1107 as Type C.

Flexural toughness	~14N/mm ² at 25°C (28 days)	
Tensile Adhesion Strength	≥ 1.15 N/mm (concrete failure)	(BS 1881)
Expansion	+0.08 % after 28 days	
Coefficient of Thermal Expansion	~11×10 ⁻⁶ per °C	

APPLICATION INFORMATION

Fresh mortar density	~ 2.2 - 2.4 kg/l (25 °C)		
Yield	~12.4-13 ltr / 25 kg bag, depending on water addition		
Layer Thickness	Min. 10 mm per pour Max.50 mm per pour		
Flowability	220 - 350 mm (Initial Flow) 180 - 250 mm (Flow after 30 min)		
Ambient Air Temperature	Min. +5°C Max. +35°C		
Mixing Ratio	Consistency	Water per 25 kg bag	W/P Ratio
	Dry pack/Trowel able	2.25 L	0.09
	Plastic Consistency (max strength)	2.50 L	0.10
	Flowable	2.75 L	0.11
	Highly Flowable (max. flow)	3.00 L	0.12
Substrate Temperature	Min. +5°C Max. +35°C		
Pot Life	~ 60 minutes (23 °C)		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ates is possible up to 100 % by weight of the dry grout powder. Trials are recommended to confirm suitability of aggregates to be employed.

- Use of aluminum tools & equipment is strongly not recommended.

LIMITATIONS

- Ensure formwork is secure and watertight to prevent movement and leaking during placing and curing.
- Where maximum thickness exceeds 75 mm, consider the use of Sikacrete®-113PP SA.
- At high temperatures, use chilled water for mixing to keep grout mix temperature below 30°C.
- In hot weather, base plates and found actions must be shaded from direct sunlight.
- Condition bags < 30 °C prior to use.
- SikaRep® SA thixotropic fine mortars can be used to fix shims and alignment plates before grouting.
- Depending on requirements and site condition, the addition of single size, clean coarse aggreg-

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Embedded steel reinforcing should be free from scale, rust, oil and grease, and treated with a suitable anti-corrosion coating such as SikaTop® Armatec®-110 EpoCem®.

The application of a suitable bonding agent such as Sikadur®-32 LP or SikaTop® Armatec®-110 EpoCem® will improve adhesion on large areas or where particularly dense concrete substrates are involved.

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surfaces should be clean, sound, rough and free from oil, grease, cement laitance and all loosely adhering particles.

Absorbent surfaces should be saturated thoroughly with clean water. Metal surfaces (iron and steel) should be free from scale, rust, oil and grease.

MIXING

Add water according to the desired consistency into a clean mixing vessel before slowly adding the SikaGrout®-114 PK SA powder. SikaGrout®-114 PK is best mixed in a forced action mixer, for 2 to 3 minutes or until the mix is free of lumps, not longer than 5 minutes. Slow speed SS paddle mixer (maximum 500 rpm) should be used for mixing (aluminum paddle is strongly not recommended). Normal tumble type concrete mixers are not suitable. Do not mix more grout than can be placed within 15 to 20 minutes. Do not add extra water or other ingredients. Mix only full bags for best results.

APPLICATION

Before pouring let the mixed grout stand for approximately 5 minutes after mixing to allow entrapped air to escape. Pour into the prepared area such that the grout has the shortest distance to travel. Ensure that air displaced by the grout is allowed to escape. When carrying out base plate grouting, ensure a sufficient head of pressure is maintained to keep the mortar flowing. All exposed areas of the mortar surface should be kept as small as possible.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

PRODUCT DATA SHEET

SikaGrout®-114 PK

July 2024, Version 02.01

020201010010000485

CURING TREATMENT

Treat exposed surfaces with Antisol®-WB curing compounds or use other approved curing methods such as polyethylene sheeting or wet hessian. Do not commence fogging until final set has been reached.

CLEANING OF TOOLS

Clean equipment and mixer immediately after application with water. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SikaGrout-114PK-en-PK-(07-2024)-2-1.pdf