BUILDING TRUST

PRODUCT DATA SHEET

Sika® Separol® WB PK

WATER BASED FORMWORK RELEASE AGENT

DESCRIPTION

Sika® Separol® WB PK is a ready-to-use, water-based mould release agent which is designed to provide easy release of formwork. It is based on a blend of refined oils, specially formulated for their high quality surface finish and stability.

USES

Sika® Separol® WB PK when applied to steel, plastic and timber formwork allows clean, fast and easy striking.

CHARACTERISTICS / ADVANTAGES

- Suitable for all types of formwork.
- Produced from refined oils, hence minimal hazards to health.
- Suspension and sediment free.
- Significantly reduces the incidence of blowholes, surface blemishes and staining.
- An effective rust inhibitor (for metal forms).
- Very economic coverage rates can be obtained.

PRODUCT INFORMATION

Packaging	05 ltr jerry can 20 ltr plastic can 200 ltr drum 1000 ltr IBC Bulk supply in tanker is possible on demand
Appearance / Colour	Milky white liquid
Shelf Life	12 months from the date of production
Storage Conditions	The product must be stored properly in undamaged, unopened original sealed packaging in dry conditions at temperatures between +5° C and +35° C. Protect from direct sunlight and frost.
Specific gravity	0.9 ± 0.02

APPLICATION INFORMATION

Consumption	In normal use, 1 L will cover approximately 30–35 m². In the case of steel and fibreglass moulds, a single application is sufficient. For untreated timber moulds being used for the first time, apply at least 2 coats to ensure that the surface is adequately sealed. Thereafter, application of a single coat is sufficient before the next cast.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Sika® Separol® WB PK is supplied ready-to-use and should not be diluted.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

All surfaces to be coated with Sika® Separol® WB PK must be clean and free from grease and other foreign materials. Sika® Separol® WB PK can be applied either by brush, roller or spray. It is supplied ready-to-use and requires only adequate stirring before application. Do not re-wet the applied coating with water even when the surface is dry. For best results, Sika® Separol® WB PK should preferably be applied under shade and concreting should take place within 2 hours of application of Sika® Separol® WB PK.

CLEANING OF TOOLS

Clean all tools and application equipment water immediately after use. Hardened or cured material can only be mechanically removed.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Pakistan (Pvt.) Limited
141-CCA Phase IV, DHA
Lahore Punjab 54792
Pakistan
phone: +92 42 3569 4266 - 67
fax: +92 42 3569 4268
http://pak.sika.com/

Sika Pakistan (Pvt.) Limited
141-CCA Phase IV, DHA
Lahore Punjab 54792
Pakistan
phone: +92 42 3569 4266 - 67
fax: +92 42 3569 4268
http://pak.sika.com/